

Product information

Sasolwax 3971

printed on: 27.06.2016

Revision: 13.04.2016

Property	Specification	Unit	Method
Dropping point	78,0 .. 84,0	°C	ASTM D3954
Oil content	0,00 .. 2,00	%	ASTM D721
Needle penetration 25 °C	25 .. 33	1/10mm	ASTM D1321
Colour Saybolt	26 .. 30		ASTM D156
Kin. viscosity 100 °C	12,0 .. 16,0	mm ² /s	ASTM D7042
BfR-conformance	Complies		BfR, 25.Empf.
Requirements USP/ microcristal	Complies		USP

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including any existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall be governed exclusively by our General Sales Conditions.

Sasol Wax GmbH

Gesellschaft mit beschränkter Haftung, Location Hamburg, Germany, Registration No. Hamburg HRB 73963

Managing Director: Edwin Vorsteveld

VAT-No. DE 118 922 039 parent company Sasol Wax Int. AG Tax No. 27/164/00088

www.sasolwax.com wax@de.sasol.com